



S7136H

Glass Reinforced Hydrocarbon Ceramic High Frequency Circuit Material

FEATURES

- Glass-reinforced hydrocarbon & ceramic dielectric
- Excellent high frequency performance due to Low dielectric tolerance and loss.
- Stable electrical properties versus frequency.
- Low Z-CTE and excellent dimensional stability.

APPLICATIONS

Microstrip and Cellular Base Station
Power Amplifiers
Antennas
LNA/LNB
High frequency wireless communication
Satellite signal transmission equipment

GENERAL PROPERTIES

Test Items	Test Method	Condition	Unit	Typical Value
Dielectric Constant Process Dk	IPC-TM-650 2.5.5.5 [1]	10GHz/23 °C	-	3.42±0.05
Dielectric Constant Design Dk	Differential phase length test	A	-	3.61
Dielectric Constant	IEC 61189-2-721 (SPDR)	10GHz/23 °C	-	3.68±0.05
Loss Tangent	IPC-TM-650 2.5.5.5	10GHz/23 °C	-	0.0030
	IEC 61189-2-721 (SPDR)	10GHz/23 °C	-	0.0035
TcDk	IEC 61189-2-721	10GHz (-40-150 °C)	ppm/°C	+50
Volume Resistivity	IPC-TM-650 2.5.17.1	A	MΩ-cm	1.1x10 ⁸
Surface Resistivity	IPC-TM-650 2.5.17.1	A	MΩ	1.6x10 ⁷
Tg	IPC-TM-650 2.4.25	DSC	°C	>280
Td	ASTM D3850	TGA (5% W.L)	°C	390
CTE (X/Y/Z-axis)	IPC-TM-650 2.4.24	TMA (30-260 °C)	ppm/°C	12/14/45
Peel Strength	IPC-TM-650 2.4.8	288 °C/10s	N/mm [lb/in]	0.72 [4.11]
Water Absorption	IPC-TM-650 2.6.2.1	D-24/23	%	0.06
Thermal Conductivity	ASTM D5470	100 °C	W/m·K	0.66
Tensile Modulus (LW/CW)	ASTM D638	A	GPa	16.1/18.5
Tensile Strength (LW/CW)	ASTM D638	A	MPa	175/245
Flexural Strength	IPC-TM-650 2.4.4	A	MPa	260
Flammability	UL-94	C-48/23/50,	Rating	V-0

All the typical value is based on the 0.508mm (0.020") specimen, and the specification sheet is based on IPC4103/11.

PRODUCT SPECIFICATION PROPEAIES

Product	Standard Thickness Offerings	Standard Panel Sizes	Standard Copper Cladding
S7136H	0.010"(0.25mm) 0.020"(0.51mm) 0.030"(0.76mm) 0.040"(1.02mm) 0.050"(1.27mm) 0.060"(1.52mm)	36"x 48" & 40"x48" & 42"x48" Additional sizes may be available upon request	HOz, 1Oz, 2Oz HTE
S7136H(CH1)[1]	0.0107"(0.27mm) 0.0207"(0.53mm) 0.0307"(0.78mm) 0.0407"(1.04mm) 0.0507"(1.29mm) 0.0607"(1.54mm)		HOz, 1Oz, Low profile copper foil

[1] For double-sided boards, S7136H(CH1) results in a thickness increase of approximately 0.0007" (18µm) and the Dk decreases by about 0.1 as the core thickness decreases from 0.0207" to 0.0107"

Remark: All the typical values listed above are for your reference only and not intended for specification. Please contact Shengyi Technology Co., Ltd. for detailed information. All rights from this data sheet are reserved by Shengyi Technology Co., Ltd.