

Lead free compatible

Tg180 high thermal reliability for Lead free compatible laminate and prepreg

## TU-752, TU-75P

TU-752 laminates are made of high quality woven E-glass coated with the epoxy resin system, which provides the laminates with UV-block characteristic, and compatibility with automated optical inspection (AOI) process. These products are suitable for boards that need to survive severe thermal cycles, or to experience excessive assembly work. TU-752 laminates exhibit excellent CTE, superior chemical resistance thermal stability and anti-CAF resistance.

### PERFORMANCE AND PROCESSING ADVANTAGES

- Lead Free compatible
- Excellent coefficient of thermal expansion
- Excellent anti-CAF capability
- Superior chemical and thermal resistance
- Fluorescence for AOI
- Optical characteristics provide UV-block property
- High interlayer bonding strength with optimum resin flow
- Low moisture absorption

### GENERAL INFORMATION

- **Industry Approvals**

IPC-4101 Type Designation	/99, /101, /126
UL Designation - ANSI Grade	FR-4
UL File Number	E1 89572
Flammability Rating	94V-0
Maximum Operating Temperature	130°C
- **Standard Availability**

Thickness: 0.002"[0.05mm] to 0.062"[1.58mm], available in sheet or panel form  
Copper Foil Cladding: 1/8 to 6oz (HTE) for built-up; 1/8 to 3oz (HTE) for double sides and H to 2oz (MLS)  
Prepregs: Available in roll or panel form  
Glass Styles: 106, 1080, 2113, 2116, 1506 and 7628, etc.

TYPICAL PROPERTY VALUES FOR TU-752 LAMINATES

PROPERTY	IPC-4101	SPEC	TYPICAL VALUES
<b>Thermal</b>			
Tg (DMA)			190 °C
Tg (DSC)			180 °C
Tg (TMA)	E-2/105+des	N/A	170 °C
Td (TGA)			350 °C
CTE x-axis	Ambient to Tg	-	11~15 ppm/°C
CTE y-axis	Ambient to Tg	-	11~15 ppm/°C
CTE z-axis	25 to 260°C	-	2.7 %
Thermal Stress, Solder Float , 288°C	A	> 10	> 60 sec
T-260	E-2/105+des	N/A	> 60 min
T-288			> 15 min
Flammability	E-24/125+des	94V-0	94V-0
<b>Electrical</b>			
Permittivity (RC 50%)			
1MHz	C-24/23/50	< 5.4	4.6
1GHz	C-24/23/50	-	4.3
Loss Tangent (RC 50%)			
1MHz	C-24/23/50	< 0.035	0.014
1GHz	C-24/23/50	-	0.013
Volume Resistivity	C-96/35/90	> 10 <sup>6</sup>	> 10 <sup>10</sup> MΩ·cm
Surface Resistivity	C-96/35/90	> 10 <sup>4</sup>	> 10 <sup>8</sup> MΩ
Electric Strength		> 30 kV/mm	> 40 kV/mm
Dielectric Breakdown Voltage		> 40 kV	> 50 kV
<b>Physical</b>			
Peel Strength, 1.0 oz. Cu foil	A	> 6	7~9 lb/inch
Flexural Strength			
Lengthwise	A	> 60,000	> 65,000 psi
Crosswise	A	> 50,000	> 55,000 psi
Bow and Twist			
0.020"~0.031"		Max 1.5	< 0.8 %
0.032"~0.065"		Max 1.0	< 0.8 %
>0.066"		Max 1.0	< 0.8 %
Dimensional Stability	E-4/105+E-2/150	< 0.03	< 0.03 %
Water Absorption	E-1/105+des+D-24/23	< 0.8	0.18 %

## NOTE:

- 1.The above testing results are based on 1.0mm (0.039") laminates.
- 2.Property values are for information purposes only and are not guaranteed.
- 3.Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.